

# Aquarius<sup>+</sup>

## uPVC SCH 40 & SCH 80 INDUSTRIAL PIPING SYSTEM PRODUCT CATALOGUE



Registered & Corporate Office : Astral Poly Technik Ltd.  
 CIN : L25200GJ1996PLC029134  
 207/1, 'Astral House', B/h Rajpath Club, Off S. G. Highway, Ahmedabad - 380059.  
 Ph: 079 6621 2000 | Fax: 079 6621 2121 | Website: www.astralpipes.com

For Enquiries: [ipd@astralpipes.com](mailto:ipd@astralpipes.com)



ASTRAL TOLL FREE  
 1800 233 7957  
 Please get in touch with us  
 between 10 a.m. to 6 p.m.

# CONTENTS



**05**

Astral, India's  
Progressive Pipe  
Company

**06**

Innovation &  
Recognitions

**07**

Marketing  
Network

**08**

Introduction

**09**

The difference  
between  
uPVC and PVC

**10**

Key  
Properties

**12**

Fields of Application  
Standards &  
Specifications

**13**

Descriptive Codes  
Important For Installers  
& Users

**14**

Technical  
Specification

**20**

uPVC Injection  
Moulded  
Class 150 Flanges

**21**

Chemical Resistance  
Chart - PVC

**27**

uPVC SCH 40 & SCH 80  
Pipes & Fittings

**28**

Installation  
Procedure

**29**

Joint  
Curing

**30**

Testing Pressure  
System  
Support Spacing  
For uPVC Pipe

**32**

Expansion and  
Contraction

**34**


Notes

**1<sup>st</sup> TO  
INTRODUCE  
CPVC  
IN INDIA**

**1<sup>st</sup> TO  
INTRODUCE  
UPVC LEAD  
FREE PIPES  
IN INDIA**

**1<sup>st</sup> TO  
INTRODUCE  
LOW NOISE  
PP DRAINAGE  
PIPES IN INDIA**

**1<sup>st</sup> TO  
INTRODUCE  
FOAMED PVC  
DRAINAGE  
PIPES IN INDIA**



**1<sup>st</sup> TO  
INTRODUCE  
LEAD FREE  
COLUMN PIPES  
IN INDIA**

**1<sup>st</sup> TO  
INTRODUCE  
POLYMER BASED  
INDUSTRIAL  
PIPING SYSTEM  
IN INDIA**

**1<sup>st</sup> TO  
INTRODUCE  
NSF APPROVED  
SOLVENT  
CEMENT  
IN INDIA**

**1<sup>st</sup> TO  
INTRODUCE  
CPVC PIPING FOR  
AUTOMATIC  
FIRE SPRINKLER  
SYSTEM IN INDIA**

# ASTRAL, INDIA'S PROGRESSIVE PIPE COMPANY

Established in 1996 with the aim to manufacture best-in-globe plastic piping systems, Astral Pipes fulfils emerging piping needs of millions of houses and adds extra mileage to India's developing real estate fraternity with the hallmark of unbeaten quality and innovative piping solutions. Keeping itself ahead of the technology curve, Astral has always been a front runner in the piping category by bringing innovation and getting rid of old, primitive and ineffective plumbing methods. Bringing CPVC in India, and pioneering in this technology, have set Astral apart and its highest quality enabled it to obtain NSF approval for its CPVC pipes and fittings. Astral went beyond the category codes by launching many industry firsts, like launching India's first lead-free uPVC pipes for plumbing as well as for stream water, just to name a few.

Astral Pipes offers the widest product range across this category when it comes to product applications. Astral Pipes is equipped with production facilities at Santej and Dholka in Gujarat, Hosur in Tamil Nadu, Ghiloth in Rajasthan and Sangli in Maharashtra to manufacture plumbing systems, drainage systems, agriculture systems, fire sprinkler piping systems, industrial piping and electrical conduit pipes with all kinds of necessary fittings.

Astral Pipes' Infrastructure division Rex offers a comprehensive product range including corrugated piping for drainage and cables, polyolefin cable channels, sewage treatment plants, plastic sheathing ducts, suction hoses, and sub-surface drainage systems. This range helps Astral to establish a strong foothold in infrastructure and agriculture sector in the constantly evolving business of piping.

In 2014, Astral forayed into the adhesives category by acquiring UK-based Seal It Services Ltd. and Kanpur based Resinova Chemie Ltd., which manufacture adhesives, sealants and construction chemicals. With five manufacturing facilities now in this business segment, Astral has strengthened its presence in the category and made rapid inroads.




**ADHESIVES**  
ANAEROBIC ADHESIVES  
**SILICONE SEALANTS**  
CONSTRUCTION CHEMICALS  
PVA **CYANOACRYLATE**  
SOLVENT CEMENTS TAPES  
POLYMERIC FILLING COMPOUND  
**EPOXY ADHESIVES  
& PUTTY**  
INDUSTRIAL ADHESIVES

**PIPING**  
**AGRICULTURE  
DRAINAGE  
INDUSTRIAL**  
URBAN INFRASTRUCTURE FIRE PROTECTION  
**PLUMBING**  
CONDUIT SURFACE DRAINAGE  
**ANCILLARY  
INSULATION**




# MARKETING NETWORK

ASTRAL has a marketing network of more than 800 distributors and 30,000 dealers spread all over India with branch offices at Mumbai, Pune, Delhi, Bengaluru, Chennai, Hyderabad, Jaipur, Lucknow and Kochi. Apart from that ASTRAL has its own warehouses at Bengaluru, Vijaywada, Hyderabad, Delhi, Ghaziabad, Kolhapur, Pune, Nagpur, Indore, Varanasi, Jaipur & Hosur to deliver the material as quick as possible. More than 400 techno marketing professionals and administrative personnel are on the board to coordinate with architects, plumbing contractors and plumbers to utilize the best plumbing techniques and to get the best from the products.



Piping unit  
KENYA



# INNOVATION & RECOGNITIONS

- First to introduce CPVC piping system in India (1999)
- First to launch lead free uPVC piping system in India (2004)
- Corp Excel- National SME Excellence Award (2006)
- First to get NSF Certification for CPVC piping system in India (2007)
- First to launch lead-free uPVC column pipes in India (2012)
- Enterprising Entrepreneur of the year (2012-13)
- Business Standard Star SME of the year (2013)
- Inc. India Innovative 100 for Smart Innovation under category of 'Technology' (2013)
- India's Most Promising Brand Award (2014)
- Value Creator Award during the first ever Fortune India Next 500 (2015)
- India's Most Trusted Pipe Brand Award (2016 & 2019)
- ET Inspiring Business Leaders of India Award (2016)
- India's Most Attractive Pipe Brand Award (2016)
- Fortune India 500 Company (2016)
- Consumer Validated Superbrands India (2017 & 2019)



# INTRODUCTION

ASTRAL have been relentless in its commitment to quality and service. Through the years, ASTRAL have broadened and enhanced its product line to serve better to the customers. ASTRAL was first to introduce CPVC pipes and fittings in Indian market and now repeating its tradition, ASTRAL is very proud to introduce Lead Free ASTM PVC Solvent Weld Industrial Piping System under the brand name Aquarius+. ASTRAL Aquarius+ ASTM PVC pipes and fittings are Lead Free and hence non toxic, easy to install and are made for life time trouble free service. ASTRAL Aquarius+ pipes and fittings are available in range of 15 mm (½") to 300 mm (12") with two different class SCH 40 and SCH 80 respectively.

As the full line leading manufacturer of CPVC pipes and fittings for residential and industrial applications and now with ASTM PVC pressure pipes and fittings, ASTRAL can be your one stop source for all the plastic piping system you require for lifetime plumbing solution.

## PVC - POLYVINYL CHLORIDE

PVC is one of the specified thermoplastic for piping system components, including valves, fittings, flanges and many speciality products. PVC has excellent chemical and corrosion resistance to a broad range of fluids.

ASTRAL PVC materials conform to ASTM Cell Classification 12454-B of ASTM D1784 (formally designated as Type I, Grade I). The maximum recommended service temperature of PVC products is 45°C (113°F)

## WHAT MAKES PVC IMPORTANT?

PVC makes a major contribution to the quality, safety and cost-effectiveness of construction materials, as well as helping to reduce the environmental impact of completed projects.

PVC is the most widely used polymer in different Industrial applications and over 50 percent of Western Europe's annual PVC production is used in this sector.

PVC has a versatility that helps to meet modern and future design needs.



# THE DIFFERENCE BETWEEN uPVC AND PVC

PVC (Poly Vinyl Chloride) is an amorphous thermoplastic material that can be compounded with additives to provide desirable properties to target a specific application. uPVC- unplasticized Poly Vinyl Chloride means Rigid PVC Pipe. Thus any Rigid PVC Pipe can be called either PVC or uPVC Pipe. PVC, uPVC or PVC-U all are different nomenclature of same material.



The images are put for representational purpose only

# KEY PROPERTIES

The key properties of ASTRAL **Aquarius+** high pressure Lead Free Industrial Piping System are significant with following features :

## **STRONG AND LIGHT WEIGHT**

ASTRAL Aquarius+ Lead Free Industrial Piping System is tough, durable with high tensile and impact strength. The system is light in weight and can be transported easily from one place to another.

## **FIRE RESISTANT**

ASTRAL Aquarius+ Lead Free Industrial Piping System is inherently difficult to ignite and stops burning once the source of heat is removed. Compared to its common plastic alternatives PVC performs better in terms of lower combustibility, flammability, flame propagation and heat release. Newly developed advantages in terms of lower acid emissions, smoke generation and enhanced fire resistance.

## **DURABLE**

ASTRAL Aquarius+ Lead Free Industrial Piping System is durable and free from weakness caused by rusting, weathering and chemical action and hence last for life time.

## **EASY TO INSTALL**

ASTRAL Aquarius+ Lead Free pipes can be cut, shaped, welded and jointed easily.

## **UV STABILIZED**

ASTRAL Aquarius+ Lead Free Industrial Piping System can be used in sunlight exposed conditions. However, ASTRAL recommends a standard grade of exterior latex paint (water base) which will protect the system adequately.

## **SAFE MATERIAL FOR DRINKING WATER**

ASTRAL Aquarius+ pipes are non-toxic and lead free which makes them a safe material for potable water. It is also the world's most researched and thoroughly tested material for uPVC which meets all international standards for safety and health for both the products and applications.

## **SIMPLE AND LEAK PROOF JOINTS**

Jointing can be done speedily with special IPS solvent cement supplied by the company which ensures 100% leak proof joints.

## **MAXIMUM FLOW RATE**

Smooth inner surface ensures high flow rate and low frictional losses. The system is leach and scale free.

## **CHEMICAL RESISTANCE**

uPVC is generally inert to most mineral acids, alkalies, salts and paraffinic hydrocarbon solutions. For more information on uPVC chemical resistance refer to Chemical Resistance of Rigid Vinyls Based.

## **WIDE RANGE**

ASTRAL Aquarius+ Lead Free Industrial Piping System available from ½" (15 mm) to 12" (300 mm) with wide range of fittings, transition fittings, valves and specially designed brass inserted fittings to suit any design criteria.

## **GOOD INSULATOR**

uPVC pipe is non conductor of electricity. ASTRAL Aquarius+ pipes are non conductor of electricity so it make the Industrial Piping System safe when working with electrical tools or equipments.

## **BENEFITS OF ASTRAL AQUARIUS+ SYSTEM OVER OTHER uPVC SYSTEMS**


**ASTRAL Aquarius+ uPVC pipes being lead free are non-toxic and hence favoured for use in applications such as potable water pipes.**

**ASTRAL Aquarius+ uPVC Industrial Piping System utilizes NSF (National Sanitation Foundation) approved one - step solvent cement, specifically formulated for the use. Joining is accomplished quickly and efficiently utilizing inexpensive tools thereby greatly reducing labor and installation costs.**


**ASTRAL Aquarius+ uPVC solvent joint Industrial Piping System makes its pressure bearing capacity twice than that of the threaded pipe.**

**ASTRAL Aquarius+ uPVC pipes & fittings exhibit the well-known physical characteristics and other benefits of conventional PVC piping such as good chemical and corrosion resistance, low thermal conductivity, high strength-to-weight ratio, good impact resistance and ease of installation.**

# FIELDS OF APPLICATION




METAL TREATING



PULP AND PAPER



SUGAR INDUSTRIES



POWER SECTOR




FERTILIZER




MINING




SHIPPING INDUSTRIES



CHEMICAL PROCESSING



STEEL INDUSTRIES



WATER TREATMENT PLANTS

# STANDARDS & SPECIFICATIONS

- ASTM D 1784** - Rigid Poly Vinyl Chloride (PVC) Compounds.
- ASTM D 1785** - Poly Vinyl Chloride (PVC) Plastic Pipes, SCH 40 & SCH 80.
- ASTM D 2466** - Socket type Poly Vinyl Chloride (PVC) Plastic Pipe Fittings, SCH 40.
- ASTM D 2467** - Socket type Poly Vinyl Chloride (PVC) Plastic Pipe Fittings, SCH 80.
- ASTM D 2564** - Solvent Cements for Plastic Pipes & Fittings
- ASTM F 1498** - Taper Pipe threads 60° for Thermoplastics Pipe & Fittings
- ASTM D 2774** - Underground Installation of Thermoplastic Pipes.
- ISO 7/1** - Pipe threads where pressure joints are made on threads -  
Part 1 : Designation, Dimension & Tolerances.

# DESCRIPTIVE CODES

- ASTM** - American Society for Testing of Materials.
- ANSI** - American National Standards Institute
- BSP** - British Standard Pipe
- IPS** - Iron Pipe Size (ASTM)
- NPT** - National Pipe Threads (ANSI)
- FIPT** - Female Iron Pipe Threads
- MIPT** - Male Iron Pipe Threads
- SOCKET** - Solvent Weld Socket
- SPIGOT** - Spigot End (IPS)
- FBSP** - Female BSP Threads
- MBSP** - Male BSP Threads
- NSF** - National Sanitation Foundation
- PVC** - Poly Vinyl Chloride
- EPDM** - Ethylene Propylene  
Diene Monomer Rubber

# IMPORTANT FOR INSTALLERS & USERS


**WATER HAMMER :** ASTRAL recommends that all uPVC Plastic piping systems be designed and constructed to avoid excessive WATER HAMMER. Water hammer can cause damage and failure to pipe, valves and fittings within the piping system.

**THREADED CONNECTIONS :** Use a quality grade thread sealant. Do not use substances that could cause stress cracking to plastic. Major attention must be given while making plastic thread joints. 1 to 2 turns beyond FINGER TIGHT is generally all that is required to make a sound plastic connection. Unnecessary OVER TIGHTENING will cause DAMAGE TO BOTH PIPES & FITTINGS. Also give proper attention while selecting the threaded fittings, as ASTRAL manufacture some fittings with NPT threads & some fittings with BSP threads to give more versatility to customer NPT threads are not compatible with BSP threads.

**SEAL & GASKET LUBRICANTS :** Some Lubricants, including vegetable oils are known to cause stress cracking in thermoplastics materials. A mild soap or commercially available pipe gasket lubricants suitable for uPVC is recommended where lubrication is required for installation or maintenance service (especially with Flange joints). Choice of lubricant is at the discretion of the installer.

**FLOW VELOCITY :** System should not be operated or flushed out at flow velocity greater than **5 feet per second.**

# TECHNICAL SPECIFICATION



## PRESSURE RATING @23°C - uPVC PIPE SCHEDULE 40 (GREY)

Product Code	Nominal Size		Average OD		Minimum Wall Thickness		Max. Work Pre. at 23°C	
	in	mm	in	mm	in	mm	PSI	kg/cm <sup>2</sup>
M061400501	½	15	0.840	21.34	0.109	2.77	600	42.19
M061400502	¾	20	1.050	26.67	0.113	2.87	480	33.75
M061400503	1	25	1.315	33.40	0.133	3.38	450	31.64
M061400504	1¼	32	1.660	42.16	0.140	3.56	370	26.01
M061400505	1½	40	1.900	48.26	0.145	3.68	330	23.20
M061400506	2	50	2.375	60.32	0.154	3.91	280	19.69
M061400507	2½	65	2.875	73.02	0.203	5.16	300	21.09
M061400508	3	80	3.500	88.90	0.216	5.49	260	18.28
M061400509	4	100	4.500	114.30	0.237	6.02	220	15.47
M061400510	6	150	6.625	168.28	0.280	7.11	180	12.66
M061400511	8	200	8.625	219.08	0.322	8.18	160	11.25
M061400512	10	250	10.750	273.05	0.365	9.27	140	9.84
M061400513	12	300	12.750	323.85	0.406	10.31	130	9.14

MPa = Mega Pascal 1 MPa = 10 kg / cm<sup>2</sup> 1 kg / cm<sup>2</sup> = 14.223343 PSI.

## PRESSURE RATING @23°C - uPVC PIPE SCHEDULE 80 (GREY)

Product Code	Nominal Size		Average OD		Minimum Wall Thickness		Max. Work Pre. at 23°C	
	in	mm	in	mm	in	mm	PSI	kg/cm <sup>2</sup>
M061800501	½	15	0.840	21.34	0.147	3.73	850	59.76
M061800502	¾	20	1.050	26.67	0.154	3.91	690	48.51
M061800503	1	25	1.315	33.40	0.179	4.55	630	44.29
M061800504	1¼	32	1.660	42.16	0.191	4.85	520	36.56
M061800505	1½	40	1.900	48.26	0.200	5.08	470	33.04
M061800506	2	50	2.375	60.32	0.218	5.54	400	28.12
M061800507	2½	65	2.875	73.02	0.276	7.01	420	29.53
M061800508	3	80	3.500	88.90	0.300	7.62	370	26.01
M061800509	4	100	4.500	114.30	0.337	8.56	320	22.50
M061800510	6	150	6.625	168.28	0.432	10.97	280	19.69
M061800511	8	200	8.625	219.08	0.500	12.7	250	17.57
M061800512	10	250	10.750	273.05	0.593	15.06	230	16.17
M061800513	12	300	12.750	323.85	0.687	17.45	230	16.17

MPa = Mega Pascal 1 MPa = 10 kg / cm<sup>2</sup> 1 kg / cm<sup>2</sup> = 14.223343 PSI.

## TEMPERATURE PRESSURE DE-RATING FACTOR

The operating pressure of PVC pipe will be reduced as the operating temperature increases above 23°C (73° F). To calculate this reduction, multiply the operating pressure with the correction factors shown below at a operating temperature of system :

Operating Temp. °C (F)	23° (73)	27° (80)	32° (90)	38° (100)	43° (110)	49° (120)	54° (130)	60° (140)
PVC	100%	90%	75%	62%	50%	40%	30%	22%


## PHYSICAL PROPERTIES OF uPVC MATERIALS

Property	Units	Value	ASTM Test Method
Specific Gravity	g / cc	1.41 - 1.46	D792
Tensile Strength (23°C)	PSI	7,200	D638
Modulus of Elasticity in Tension (23°C)	PSI	4,60,000	D638
Flexural Strength (23°C)	PSI	13,200	D790
Izod Impact (Notched at 23°C)	ft lb/in.	0.65	D256
Hardness (Durometer D)	---	80 ± 3	D2240
Hardness (Rockwell R)	---	110 - 120	D785
Compressive Strength (23°C)	PSI	9,000	D695
Hydrostatic Design Stress	PSI	2,000	D1598
Coefficient of Linear Expansion	in./in./°F	3.1 x 10 <sup>-5</sup>	D696
Heat Deflection Temperature at 66 psi	degrees °F	165	D648
Coefficient of Thermal Conductivity	BTU/hr/sq. ft/°F/in.	1.2	D177
Specific Heat	BTU/F/lb	0.25	D2766
Limiting Oxygen Index	%	43	D2863
Water Absorption (24 hrs at 23°C)	% weight gain	0.05	D570
Cell Classification-Pipe	---	12454-B	D1784
Cell Classification-Fittings	---	12454-B	D1784

Above data is based upon information provided by the raw material manufacturers. It should be used only as a recommendation and not as a guarantee of performance.




# uPVC SCHEDULE 40



## PIPE DIMENSIONS

Nominal Pipe Size		Mean Outside Diameter		O.D. Tolerance		Minimum Wall Thickness	
in	mm	in	mm	in	mm	in	mm
½	12.7	0.840	21.34	.004	0.10	0.109	2.77
¾	19.05	1.050	26.67	.004	0.10	0.113	3.38
1	25.4	1.315	33.04	.005	0.13	0.133	3.38
1¼	31.75	1.660	42.16	.005	0.13	0.140	3.56
1½	38.1	1.900	48.26	.006	0.15	0.145	3.68
2	50.8	2.375	60.33	.006	0.15	0.154	3.91
2½	63.5	2.875	73.03	.007	0.18	0.203	5.16
3	76.2	3.500	88.9	.008	0.20	0.216	5.49
4	101.6	4.500	114.3	.009	0.23	0.237	6.02
5	127.0	5.563	141.3	.010	0.25	0.258	6.55
6	152.4	6.625	168.28	.011	0.28	0.280	7.11
8	203.2	8.625	219.08	.015	0.38	0.322	8.18
10	254.0	10.750	273.05	.015	0.38	0.365	9.27
12	304.8	12.750	323.85	.015	0.38	0.408	10.36

# uPVC SCHEDULE 80



## PIPE DIMENSIONS

Nominal Pipe Size		Mean Outside Diameter		O.D. Tolerance		Minimum Wall Thickness	
in	mm	in	mm	in	mm	in	mm
½	12.7	0.840	21.34	.004	0.10	0.14	3.73
¾	19.05	1.050	26.67	.004	0.10	0.15	3.91
1	25.4	1.315	33.04	.005	0.13	0.17	4.54
1¼	31.75	1.660	42.16	.005	0.13	0.19	4.85
1½	38.1	1.900	48.26	.006	0.15	0.20	5.08
2	50.8	2.375	60.33	.006	0.15	0.21	5.53
2½	63.5	2.875	73.03	.007	0.18	0.27	7.01
3	76.2	3.500	88.9	.008	0.20	0.30	7.62
4	101.6	4.500	114.3	.009	0.23	0.33	8.55
5	127.0	5.563	141.3	.010	0.25	0.37	9.52
6	152.4	6.625	168.28	.011	0.28	0.43	10.97
8	203.2	8.625	219.08	.015	0.38	0.50	12.7
10	254.0	10.750	273.05	.015	0.38	0.59	15.06
12	304.8	12.750	323.85	.015	0.38	0.68	17.44

Moulded Schedule 80 fittings are manufactured to ASTM D 2467 for use with pipe manufactured to ASTM D1785.




The images are put for representational purpose only



The images are put for representational purpose only


# uPVC SCHEDULE 80



## SOCKET DIMENSIONS OF FITTINGS

Nominal Pipe Size		Diameter				Socket Length			
Entrance A		Bottom B		Tolerance A		Minimum C			
in	mm	in	mm	in	mm	in	mm		
½	12.7	0.848	21.54	0.836	21.23	.004	0.10	0.688	17.48
¾	19.05	1.058	26.87	1.046	26.57	.004	0.10	0.719	18.26
1	25.4	1.325	33.66	1.310	33.27	.005	0.13	0.875	22.23
1¼	31.75	1.670	42.42	1.655	42.04	.005	0.13	0.938	23.83
1½	38.1	1.912	48.56	1.894	48.11	.006	0.15	1.094	27.79
2	50.8	2.387	60.63	2.369	60.17	.006	0.15	1.156	29.36
2½	63.5	2.889	73.38	2.868	72.85	.007	0.18	1.750	44.45
3	76.2	3.516	89.31	3.492	88.7	.008	0.20	1.875	47.63
4	101.6	4.518	114.76	4.491	114.07	.009	0.23	2.000	50.8
5	127.0	5.583	141.81	5.553	141.05	.010	0.25	3.000	76.2
6	152.4	6.647	168.83	6.614	168.00	.011	0.28	3.000	76.2
8	203.2	8.655	219.84	8.610	218.69	.015	0.38	4.000	101.6
10	254.0	10.780	273.81	10.735	272.67	.015	0.38	5.000	127.0
12	304.8	12.780	327.61	12.735	323.47	.015	0.38	6.000	152.4

Moulded Schedule 80 fittings are manufactured to ASTM D 2467 for use with pipe manufactured to ASTM D1785.



## BSPT THREAD DIMENSIONS

Nominal Pipe Size		Threads Per Inch	Pitch of Thread P	
in	mm		in	mm
½	12.7	14	0.0714	1.814
¾	19.05	14	0.0714	1.814
1	25.4	11	0.0909	2.309
1¼	31.75	11	0.0909	2.309
1½	38.1	11	0.0909	2.309
2	50.8	11	0.0909	2.309
2½	63.5	11	0.0909	2.309
3	76.2	11	0.0909	2.309
4	101.6	11	0.0909	2.309
5	127	11	0.0909	2.309
6	152.4	11	0.0909	2.309
8	203.2	10	0.100	2.540
10	254	10	0.100	2.540
12	304.8	8	0.125	3.175



The images are put for representational purpose only

## STANDARD COMPARISONS

JIS K6741 (mm)		DIN 8062 (mm)		ASTM F 441 (in)		NPT – ANSI B1.20.1** Tapered Thread		BSP – BS21, DIN 2999, ISO 7/1 Thread	
Nominal	Actual*	O.D.	Actual*	Nominal	Actual*	Designation	Threads/in.	Designation	Threads/25.4mm
16	22	20	20	½	0.840	½	14.0	½	14.0
20	26	25	25	¾	1.050	¾	14.0	¾	14.0
25	32	32	32	1	1.315	1	11.5	1	11.0
30	38	40	40	1¼	1.660	1¼	11.5	1¼	11.0
40	48	50	50	1½	1.900	1½	11.5	1½	11.0
50	60	63	63	2	2.375	2	11.5	2	11.0
75	89	90	90	3	3.500	3	8.0	3	11.0
100	114	110	110	4	4.500	4	8.0	4	11.0

\*Specified dimension, certain tolerances apply

\*\*NPT and BSP have different thread angles and not compatible.

# uPVC INJECTION MOULDED CLASS 150 FLANGES

## TECHNICAL INFORMATION

### APPLICATION

CLASS 150 Flange fittings are coupling devices designed for joining IPS (Iron Pipe Size) plastic piping systems, where frequent disassembly may be required, and can be used as a transitional fitting for joining plastic to metal piping systems. Suitability of application is at the discretion of the user.

### PRESSURE RATING

150 psi, water at 73°F.

### FLANGE TYPES

- One Piece** – Available in socket configuration, sizes ½" through 12".
- Van Stone Style** – Two-piece design with rotating flange ring, available in socket configurations, sizes ½" to 12".
- Blind** – Closed ring design for capping off a mating flange, flanged fitting or flanged valve, available in sizes ½" to 12".

### MATERIALS

All injection mould flanges are produced from uPVC materials approved for potable water use.

Glass-filled uPVC mould materials may be used in certain Van Stone Style flange-rings and large diameter Blind flanges where additional reinforcement is deemed necessary.

### CONFORMANCE STANDARDS

- Socket & Spigot** – ASTM D2467 (uPVC)
- Threads** – ASTM F1498
- Bolt Hole Pattern** – ANSI B16.5; ASTM D4024
- Material** – ASTM D1784 (uPVC Cell Classification 12454-B)

# CHEMICAL RESISTANCE CHART - PVC

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
[A]		
Acetaldehyde	NR	NR
Acetic Acid, pure	NR	NR
Acetic Acid, 10%	R	R
Acetic Acid, 20%	R	R
Acetic Acid, 80%	R	R
Acetic Acid, Glacial	R	NR
Acetic Anhydride	NR	NR
Acetone	NR	NR
Acetyl Nitrile	NR	NR
Acetylene	R	R
Acrylic Acid Ethyl Ester	NR	NR
Adipic Acid	R	R
Alcohols Methyl	R	R
Butyl	R	NR
Propyl	R	R
Allyl Alcohol, 96%	R	NR
Allyl Chloride	R	R
Alum	R	R
Alum, Chrome	R	R
Alum, Potassium	R	R
Aluminum Alum	R	R
Aluminum Chloride	R	R
Aluminum Fluoride	R	R
Aluminum Hydroxide	R	R
Aluminum Oxylchloride	R	R
Aluminum Nitrate	R	R
Aluminum Sulfate	R	R
Ammonia (Gas-dry)	R	R
Ammonia (Liquid)	NR	NR
Ammonium Acetate	R	R
Ammonium Alum	R	R
Ammonium Bifluoride	R	R
Ammonium Bisulfate	R	R
Ammonium Carbonate	R	R
Ammonium Chloride	R	R
Ammonium Dichromate	R	NR
Ammonium Fluoride, 25%	R	NR
Ammonium Hydroxide	R	R
Ammonium Hydroxide, 10%	R	R
Ammonium Hydroxide, 28%	R	R
Ammonium Metaphosphate	R	R
Ammonium Nitrate	R	R
Ammonium Persulfate	R	R
Ammonium Phosphate	R	R
Ammonium Sulfate	R	R
Ammonium Sulfide	R	R
Ammonium Thiocyanate	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
[A]		
Amyl Acetate	NR	NR
Amyl Alcohol	R	NR
Amyl Chloride	NR	NR
Aniline	NR	NR
Aniline Chlorohydrate	NR	NR
Aniline Hydrochloride	NR	NR
Anthraquinone	R	NR
Anthraquinonesulfonic Acid	R	R
Antimony Trichloride	R	R
Aqua Regia	NR	NR
Aromatic Hydrocarbons	NR	NR
Arsenic Acid, 80%	R	R
Arylsulfonic Acid	R	R
[B]		
Barium Nitrate	R	R
Barium Carbonate	R	R
Barium Chloride	R	R
Barium Hydroxide (10%)	R	R
Barium Sulfate	R	R
Barium Sulfide	R	R
Beer	R	R
Beet Sugar Liquors	R	R
Benzaldehyde, 10%	R	NR
Benzaldehyde, above 10%	NR	NR
Benzene	NR	NR
Benzoic Acid	R	R
Bismuth Carbonate	R	R
Black Liquor	R	R
Bleach (12% Cl)	R	R
Borax	R	R
Boric Acid	R	R
Breeder Pellets (Fish deriv.)	R	R
Brine (Acid)	R	R
Bromic Acid	R	R
Bromine, Liquid	NR	NR
Bromine, Vapor (25%)	R	R
Bromine Water	R	R
Bromine Water	NR	NR
Bromobenzene	NR	NR
Bromotoluene	NR	NR
Butadiene	R	R
Butane	R	R
Butanol, Primary	R	R
Butanol, Secondary	R	NR
Butyl Acetate	R	NR
Butyl Alcohol	R	R
Butyl Cellosolve	R	NR

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[B]</b>		
Butyl Mercaptan	NR	NR
Butyl Phenol	R	NR
Butyl Stearate	R	NR
Butynediol	R	NR
Butyric Acid	R	NR
<b>[C]</b>		
Cadmium Cyanide	R	R
Calcium Bisulfide	R	R
Calcium Bisulfite	R	R
Calcium Bisulfite Bleach Liquor	R	R
Calcium Carbonate	R	R
Calcium Chlorate	R	R
Calcium Chloride	R	R
Calcium Hydroxide	R	R
Copper Hypochlorite	R	R
Calcium Nitrate	R	R
Calcium Oxide, Type I	R	R
Calcium Sulfate	R	R
Camphor (Crystals)	R	NR
Cane Sugar Liquors	R	R
Carbitol	R	NR
Carbon Dioxide	R	R
Carbon Dioxide-Aqueous Solution	R	R
Carbon Disulfide	NR	NR
Carbon Monoxide	R	R
Carbon Tetrachloride	R	NR
Carbon Tetrachloride	NR	NR
Carbonic Acid	R	R
Castor Oil	R	R
Caustic Potash	R	R
Cellosolve	R	NR
Cellosolve Acetate	R	NR
Chloracetic Acid, Type I	R	R
Chloracetic Acid, Type II	R	NR
Chloral Hydrate	R	R
Chloramine	R	NR
Chloric Acid, 20%	R	R
Chloride (Water)	R	R
Chlorinated Solvents	NR	NR
Chlorine (Dry-liquid)	NR	NR
Chlorine (Liquid) (under pressure)	NR	NR
Chlorine Gas (Dry)	NR	NR
Chlorine Gas (Wet)	NR	NR
Chlorine Water	R	NR
Chloroacetic Acid	R	R
Chloroacetyl Chloride	R	NR
Chlorobenzene	NR	NR
Chloroform	NR	NR
Chloropicrin	NR	NR
Chlorosulfonic Acid	R	NR

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[C]</b>		
Chlorox Bleach Solution	R	R
Chrome Alum	R	R
Chromic Acid, 10%	R	NR
Chromic Acid, 50%	NR	R
Chromic/Nitric Acid	R	NR
15%-35%	NR	NR
Chromic/Sulfuric/Water	R	NR
50/15/35	R	R
Citric Acid	R	R
Coconut Oil Alcohol	R	R
Copper Carbonate	R	R
Copper Chloride	R	R
Copper Cyanide	R	R
Copper Fluoride	R	R
Copper Nitrate	R	R
Copper Sulfate	R	R
Corn Syrup	R	R
Cottonseed Oil	R	NR
Cresol	NR	R
Cresylic Acid, 50%	R	NR
Crotonaldehyde	NR	R
Crude Oil	R	R
Cupric Fluoride	R	R
Cupric Sulfate	R	R
Cuprous Chloride	R	R
Cyclanones	R	NR
Cyclohexane	NR	NR
Cyclohexanol	NR	NR
Cyclohexanone	NR	NR
<b>[D]</b>		
D.D.T. (Xylene Base)	NR	NR
Desocyphephedrine Hydrochloride	R	R
Detergents	R	R
Dextrin	R	R
Dextrose	R	R
Diacetone Alcohol	R	R
Diazo Salts	R	NR
Dibutoxy Ethyl Phthalate	NR	NR
Dibutyl Phthalate	NR	NR
Dibutyl Sebacate	R	NR
Dichlorobenzene	NR	NR
Diesel Fuels	R	R
Diethyl Ether	R	R
Diglycolic Acid	R	NR
Dimethyl Hydrazine	NR	R
Dimethylamine	R	NR
Diocetylphthalate	NR	NR
Disodium Phosphate	R	R
Distilled Water	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[E]</b>		
Esters	NR	NR
Ethers	NR	NR
Ethyl Acetate	NR	NR
Ethyl Acrylate	NR	NR
Ethyl Alcohol	R	R
Ethyl Chloride	NR	NR
Ethyl Chloroacetate	NR	NR
Ethyl Ether	NR	NR
Ethylene Bromide	NR	NR
Ethylene Chlorohydrin	NR	NR
Ethylene Dichloride	NR	NR
Ethylene Glycol	R	R
Ethylene Oxide	NR	NR
<b>[F]</b>		
Fatty Acids	R	R
Ferric Acetate	R	NR
Ferric Chloride	R	R
Ferric Hydroxide	R	R
Ferric Nitrate	R	R
Ferric Sulfate	R	R
Ferrous Chloride	R	R
Ferrous Hydroxide	R	NR
Ferrous Nitrate	R	R
Ferrous Sulfate	R	R
Fish Solubles	R	R
Fluoroboric Acid	R	R
Fluorine Gas (Wet)	R	NR
Fluorine Gas	R	NR
Fluorine Gas, T	NR	NR
Fluorosilicic Acid, 25%	R	R
Formaldehyde	R	R
Formic Acid	R	NR
Fructose	R	R
Fruit Juices and Pulp	R	R
Furfural	NR	NR
Freon II	R	R
Freon 12	R	R
Freon 21	NR	NR
Freon 22	NR	NR
Freon 113	R	NR
Freon 114	R	R
<b>[G]</b>		
Gallic Acid	R	R
Gas (Coke Oven)	NR	NR
Glucose	R	R
Glycerine	R	R
Glycol	R	R
Glycolic Acid	R	R
Grapesugar	R	R
Green Liquor	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[H]</b>		
Heptane	R	R
Hexane	R	NR
Hexanol, Tertiary	R	R
Hydrobromic Acid, 20%	R	R
Hydrochloric Acid, 10%	R	R
Hydrochloric Acid, 30%	R	R
Hydrochloric Acid	R	R
Conc.	R	NR
Hydrochloric Acid Pickling	R	R
Hydrocyanic Acid	R	R
Hydrofluoric Acid, 48%	R	NR
Hydrofluoric Acid, 50%	R	NR
Hydrofluoric Acid, 70%	NR	NR
Hydrofluorsilicic Acid	R	R
Hydrogen	R	R
Hydrogen Peroxide, 30%	R	R
Hydrogen Peroxide, 50%	R	R
Hydrogen Peroxide, 90%	R	R
Hydrogen Phosphide	R	R
Hydrogen Sulfide	R	R
Hydroquinone	R	R
Hydroxylamine Sulfate	R	R
Hypochlorine Acid	R	R
Hypochlorous Acid	R	R
Hydrazine (Anhydrous) 97%	NR	NR
<b>[I]</b>		
Iodine	NR	NR
Iodine Solution (10%)	NR	NR
<b>[K]</b>		
Kerosene	R	R
Ketones	NR	NR
Kraft Liquors	R	R
<b>[L]</b>		
Lactic Acid, 25%	R	R
Lactic Acid, 80%	R	R
Lard Oil	R	R
Lauric Acid	R	R
Lauryl Chloride	R	R
Lead Acetate	R	R
Lead Chloride	R	R
Lead Nitrate	R	R
Lead Sulfate	R	R
Linoleic Acid	R	R
Linoleic Oil	R	R
Linseed Oil	R	R
Liquors	R	R
Lithium Bromide	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[M]</b>		
Machine Oil	R	R
Magnesium Carbonate	R	R
Magnesium Chloride	R	R
Magnesium Citrate	R	R
Magnesium Hydroxide	R	R
Magnesium Nitrate	R	R
Magnesium Sulfate	R	R
Manganese Chloride	R	R
Manganese Sulfate (Sat.)	R	R
Manganese Sulfate (10%)	R	R
Manganese Sulfate (20%)	R	R
Maleic Acid	R	R
Malic Acid	R	R
Mercural Ointment, Blue (5%)	R	R
Mercuric Chloride	R	R
Mercuric Cyanide	R	R
Mercurous Nitrate	R	R
Mercury	R	R
Mercury Ointment (Ammoniated)	R	NR
Methoxyethyl Oleate	R	R
Methyl Alcohol	R	NR
Methyl Cellosolve	NR	NR
Methyl Chloride	NR	NR
Methyl Ethyl Ketone	NR	NR
Methyl Iso-Butyl Ketone	NR	NR
Methyl Methacrylate	R	NR
Methyl Salicylate	R	NR
Methyl Sulfate	R	R
Methyl Sulfuric Acid	R	R
Methylamine	NR	NR
Methylene Bromide	NR	NR
Methylene Chloride	NR	NR
Methylene Iodine	NR	NR
Milk	R	R
Mineral Oils	R	R
Mixed Acids	R	R
Molasses	R	R
Muriatic Acid	R	R
<b>[N]</b>		
Naphtha	R	R
Naphthalene	NR	NR
Natural Gas	R	R
Nickel Acetate	R	R
Nickel Chloride	R	R
Nickel Nitrate	R	R
Nickel Sulfate	R	R
Nicotine	R	R
Nicotine Acid	R	R
Nitric Acid, Anhydrous	NR	NR
Nitric Acid, 10%	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[N]</b>		
Nitric Acid, 30%	R	R
Nitric Acid, 60%	R	R
Nitric Acid, 68%	R	NR
Nitrobenzene	NR	NR
Nitroglycerine	NR	NR
Nitrous Oxide	R	NR
Nitroglycol	NR	NR
<b>[O]</b>		
Ocenol, Type I	R	R
Oils and Fats	R	R
Oils, Sour Crude	R	R
Oleic Acid	R	R
Oleum	NR	NR
Oxalic Acid	R	R
Oxygen	R	R
Ozone	R	R
<b>[P]</b>		
Palmitic Acid, 10%	R	R
Palmitic Acid, 70%	R	NR
Paraffin	R	R
Peracetic Acid, 40%	R	NR
Perchloric Acid, 10%	R	R
Perchloric Acid, 15%	R	NR
Perchloric Acid, 70%	R	NR
Perphosphate	R	R
Petroleum Liquifier	R	R
Petroleum Oils (Sour)	R	NR
Phenol	NR	NR
Phenylhydrazine	NR	NR
Phenylhydrazine Hydrochloride	NR	NR
Phosgene, Liquid	NR	NR
Phosgene, Gas	R	R
Phosphoric Acid, 10%	R	R
Phosphoric Acid, 25%	R	R
Phosphoric Acid, 50%	R	R
Phosphoric Acid, 75%	R	R
Phosphoric Acid, 85%	R	R
Phosphorous (Yellow)	R	NR
Phosphorous Pentoxide	R	NR
Phosphorous Trichloride	NR	NR
Picric Acid	NR	NR
Potash (Sat. Aq.)	R	R
Potassium Alum	R	R
Potassium Amyl Xanthate	R	NR
Potassium Bicarbonate	R	R
Potassium Bisulfate	R	R
Potassium Borate	R	R
Potassium Bromate	R	R
Potassium Bromide	R	R
Potassium Carbonate	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[P]</b>		
Potassium Chromate	R	R
Potassium Chlorate	R	R
Potassium Chloride	R	R
Potassium Cyanide	R	R
Potassium Dichromate	R	R
Potassium Ethyl Xanthate	R	NR
Potassium Ferricyanide	R	R
Potassium Ferrocyanide	R	R
Potassium Fluoride	R	R
Potassium Hydroxide	R	R
Potassium Nitrate	R	R
Potassium Perborate	R	R
Potassium Perchlorate	R	R
Potassium Permanganate, 10%	R	R
Potassium Persulfate	R	R
Potassium Sulfate	R	R
Propane	R	R
Propane Gas	R	R
Propargyl Alcohol	R	R
Propyl Alcohol	R	R
Propylene Dichloride	NR	NR
Plating Solutions:		
Brass	R	R
Cadmium	R	R
Copper	R	R
Gold	R	R
Indium	R	R
Lead	R	R
Nickel	R	R
Rhodium	R	R
Silver	R	R
Plating Solutions (continued):		
Tin	R	R
Zinc	R	R
Pyridine,	NR	NR
Pyrogalllic Acid	R	NR
Propylene Oxide	NR	NR
<b>[R]</b>		
Rayon Coagulating Bath	R	R
Refinery Crudes	R	R
Rochelle Salts	R	R
<b>[S]</b>		
Salicylic Acid	R	R
Sea Water	R	R
Selenic Acid	R	R
Sewerage	R	R
Silicic Acid	R	R
Silver Cyanide	R	R
Silver Nitrate	R	R
Silver Plating Solution	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[S]</b>		
Silver Sulfate	R	R
Soaps	R	R
Sodium Acetate	R	R
Sodium Alum	R	R
Sodium Benzoate	R	R
Sodium Bicarbonate	R	R
Sodium Bichromate	R	R
Sodium Bisulfate	R	R
Sodium Bisulfite	R	R
Sodium Bromide	R	R
Sodium Carbonate	R	R
Sodium Chlorate	R	NR
Sodium Chloride	R	R
Sodium Chlorite	NR	NR
Sodium Cyanide	R	R
Sodium Dichromate	R	R
Sodium Ferricyanide	R	R
Sodium Ferrocyanide	R	R
Sodium Fluoride	R	R
Sodium Hydroxide, 10%	R	R
Sodium Hydroxide, 30%	R	R
Sodium Hydroxide, 50%	R	R
Sodium Hypochlorite	R	R
Sodium Nitrate	R	R
Sodium Nitrite	R	R
Sodium Peroxide, 8750	R	R
Sodium Perchlorate	R	R
Sodium Sulfate	R	R
Sodium Sulfide	R	R
Sodium Sulfite	R	R
Sodium Thiosulfate	R	R
Sour Crude Oil (West Texas)	R	R
Stannic Chloride	R	R
Stannous Chloride	R	R
Starch	R	R
Stearic Acid	R	R
Stoddards Solvent	NR	NR
Succinic Acid	R	R
Sulfite Liquor	R	R
Sulfur	R	R
Sulfur Dioxide, (Dry)	R	R
Sulfur Dioxide, (Wet)	R	NR
Sulfur Trioxide	R	R
Sulfuric Acid, 3%	R	R
Sulfuric Acid, 10%	R	R
Sulfuric Acid, 20%	R	R
Sulfuric Acid, 33%	R	R
Sulfuric Acid, 50%	R	R
Sulfuric Acid, 70%	R	NR
Sulfuric Acid, 80%	R	NR

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[S]</b>		
Sulfuric Acid, 85%	R	R
Sulfuric Acid, 90%	R	NR
Sulfuric Acid, 95%	R	NR
Sulfuric Acid Pickling	R	R
Sulfuric/Nitric (50/50)	NR	NR
Sulfurous Acid	R	R
<b>[T]</b>		
Tall Oil	R	R
Tannic Acid	R	R
Tanning Liquors	R	R
Tartaric Acid	R	R
Tetra Sodium Pyrophosphate	R	R
Tetraethyl Lead	R	NR
Tetrahydrodurane	NR	NR
Thionyl Chloride	NR	NR
Thread Cutting Oil	R	R
Tirpineol	R	NR
Titanium Tetrachloride	R	NR
Toluol or Toluene	NR	NR
Transformer Oil	R	R
Tributyl Phosphate	NR	NR
Tributyl Citrate	R	NR
Trichloroacetic Acid	R	NR
Trichloroethylene	NR	NR
Triethanolamine	R	NR
Trilones	NR	NR
Trimethyl Propane	R	R
Trisodium Phosphate	R	R
Turpentine	R	R
Trimethylamine	R	R

REAGENT	TEMPERATURE	
	23°C (73°F)	45°C (113°F)
<b>[U]</b>		
Urea	R	R
Urine	R	R
<b>[V]</b>		
Vaseline	NR	NR
Vegetable Oil	R	R
Vinegar	R	R
Vinyl Acetate	NR	NR
<b>[W]</b>		
Water Acid Mine	R	R
Water Deionized	R	R
Water Demineralized	R	R
Water Distilled, Water Fresh	R	R
Water Salt	R	R
Whiskey	R	R
White Liquor	R	R
Wines	R	R
<b>[X]</b>		
Xylene or Xylol	NR	NR
<b>[Z]</b>		
Zinc Chloride	R	R
Zinc Nitrate	R	R
Zinc Sulfate	R	R

R - Recommended  
NR - Not Recommended

# uPVC SCH 40 & SCH 80 PIPES & FITTINGS



SCH-40




SCH-80



TEE (SOC)



REDUCER TEE (SOC)



90° ELBOW - SOC



CROSS (SOC)



REDUCER COUPLING (SOC)




ELBOW 45° (SOC)



COUPLER (FAPT)



MAPT (PVC THREAD)



COUPLER (SOC)




CAP (SOC)



FLANGE HUB SOC



CLAMP SADDLE



REDUCER BUSHING (SPIG x SOC)



UNION




BUTTERFLY VALVE VITON W/HANDLE



DIAPHRAGM VALVE FLANGED EPDM



BALL VALVE



BLIND FLANGE




VANSTONE FLANGE (SOC)



FLANGE - SPIG



P-70 PRIMER



705 PVC



717 PVC


# INSTALLATION PROCEDURE

Systems should be installed in a good and workmanlike manner consistent with normal industry standards and in conformance with all local safety, fire and Industrial code requirements. Failure to follow proper installation practices, procedures or techniques can result in system failure, property damage or personal injury. Follow manufacturers' instructions for all related products.

## PIPE CUTTING

Cut pipe square. As joints are sealed at the base of the fitting socket. An angled cut may result in joint failure.

Acceptable tools include miter saw, mechanical cut off saw or wheel cutter. Wheel type cutters must employ a blade designed for plastics.



## 2 REMOVE BURR AND BEVEL




Remove all burr from inside and outside of pipe with a file, or deburring tool. Chamfer (bevel) the end of the pipe 10°-15°

CLEAN : Remove surface dirt, grease, or moisture with a clean dry cloth.

## DRY FIT

With light pressure, pipe should go one third to one half of the way into the fitting socket. Pipes and fittings that are too tight or too loose should not be used.



## 4 APPLICATOR



Use an applicator that is one half the pipe diameter.

- Too large an applicator will force excessive cement into the inside of small diameter fittings.
- Too small an applicator will not apply sufficient cement to large diameter systems.

## CEMENT

Apply a full even layer of cement to the outside of a pipe and medium layer of cement to the inside of a fitting.



## 6 JOIN PIPE AND FITTINGS



Assemble pipe and fitting socket till it contacts socket bottom. Give pipe a quarter turn. Hold pipe and fitting together until the pipe does not back out.

- Remove excessive cement from the exterior. A properly made joint will show a continuous bead of cement around the perimeter.

## uPVC CEMENT FOR SCH 40 AND INTERFERENCE FIT

Pipe Size		Cement Type	Min. Vis. (CP)	IPS - Weld On
Inch	mm			
½ - 2	15 - 50	Medium Bodied	500	705
2½ - 12	65 - 300	Heavy Bodied	1600	717

## uPVC CEMENT FOR SCH 80 AND NON INTERFERENCE FIT

Pipe Size		Cement Type	Min. Vis. (CP)	IPS - Weld On
Inch	mm			
½ - 1¼	15 - 32	Medium Bodied	500	705
1½ - 12	40 - 300	Heavy Bodied	1600	717

N.B. : Primers must be used in solvent cement joints of uPVC plastic pipe and fittings for size above 2".

# JOINT CURING

## RECOMMENDED INITIAL SET TIMES

TEMPERATURE RANGE	PIPE SIZE			
	½" to 1¼"	1½" to 3"	4" to 8"	10" to 12"
	15 to 32 mm	40 to 80 mm	100 to 200 mm	250 to 300 mm
15.5°C - 37.7°C	15 min.	30 min.	1 hrs.	2 hrs.
4.4°C - 15.5°C	1 hrs.	2 hrs.	4 hrs.	8 hrs.

## RECOMMENDED INITIAL CURE TIMES

TEMPERATURE RANGE	PIPE SIZE			
	½" to 1¼"	1½" to 3"	4" to 8"	10" to 12"
	15 to 32 mm	40 to 80 mm	100 to 200 mm	250 to 300 mm
15.5°C - 37.7°C	6 hrs.	12 hrs.	24 hrs.	48 hrs.
4.4°C - 15.5°C	12 hrs.	24 hrs.	48 hrs.	96 hrs.

# TESTING PRESSURE SYSTEM

1. Conduct pressure testing with water. DO NOT USE AIR OR OTHER GASES for pressure testing.
2. The piping system should be adequately anchored to limit movement. Water under pressure exerts thrust forces in piping systems. Thrust blocking should be provided at changes of direction, change in size and at dead ends.
3. Please refer tables given for initial set & cure times before pressure testing.
4. The piping systems should be slowly filled with water, taking care to prevent surge and air entrapment. The flow velocity should not exceed 1 feet per second.
5. All trapped air must be slowly released. Vents must be provided at all high points of the piping system. All valves and air relief mechanisms should be opened so that the air can be vented while the system is extremely dangerous and it must be slowly and completely vented prior to testing.

**For sizes 4" & above, ASTRAL recommends to use automatic air relief valves at every 300 - 400 mtr. distance & at furthest & highest points of pipeline to avoid any damage to the piping system.**

6. The piping system can be pressurized to 125% of its designed working pressure. However care must be taken to ensure the pressure does not exceed the working pressure of the lowest rated component in the system (valves, unions, flanges, threaded parts etc.)
7. The pressure test should not exceed one hour. Any leaking joints or pipe must be cut out and replaced and the line recharged and retested using the same procedure.

# SUPPORT SPACING FOR uPVC PIPE

Adequate supports for any piping system is a matter of great importance. In practice, support spacings are a function of pipe size operating temperatures, the location of heavy valves or fittings and the mechanical properties of the pipe material.

To ensure the satisfactory operation of a ASTRAL Aquarius+ uPVC piping system, the location and type of hangers should be carefully considered. Hangers should not compress, distort, cut or abrade the piping.

All piping should be supported with an approved hanger at intervals sufficiently close to maintain correct pipe alignment and to prevent sagging or geade reversal. Pipe should also be supported at all branch ends and at all changes of direction. Support trap arms as close as possible to the trap.

- (1) Concentrated loads should be supported directly so as to eliminate high stress concentrations. Should this be impractical then the pipe must be supported immediately adjacent to the load.
- (2) In systems where large fluctuations in temperature occur, allowances must be made for expansion and contraction of the piping system. Since changes in direction in the system are usually sufficient to allow for expansion and contraction hangers must be placed so as not to restrict this movement.
- (3) Since plastic pipe expands or contracts approximately five times greater than those of steel, hangers should not restrict this movement.
- (4) Hangers should provide as much bearing surface as possible. To prevent damage to the pipe, file smooth any sharp edges or burrs on the hangers or supports.
- (5) Support spacing for horizontal piping systems is determined by the maximum operating temperature the system will encounter. The piping should be supported on uniform centers with supports that do not restrict the axial movement.
- (6) For vertical lines, it is recommended that an engineer should design the vertical supports according to the vertical load involved.

**SCHEDULE - 40** RECOMMENDED SUPPORT SPACING (IN FEET)

Nom. Pipe Size		TEMPERATURE °C				
(in)	(mm)	15.5	26.6	37.7	48.8	60
½	15	4½	4½	4	2½	2½
¾	20	5	4½	4	2½	2½
1	25	5½	5	4½	3	2½
1¼	32	5½	5½	5	3	3
1½	40	6	5½	5	3½	3
2	50	6	5½	5	3½	3
2½	65	6½	6	5½	4	3
3	80	7	7	6	4	3½
4	100	7½	7	6½	4½	4
6	150	8½	8	7½	5	4½
8	200	9½	9	8½	5½	5
10	250	10½	9½	9	6½	5½
12	300	12	10½	9½	7	6

**SCHEDULE - 80** RECOMMENDED SUPPORT SPACING (IN FEET)

Nom. Pipe Size		TEMPERATURE °C				
(in)	(mm)	15.5	26.6	37.7	48.8	60
½	15	5	4½	4½	3	2½
¾	20	5½	5	4½	3	2½
1	25	6	5½	5	3½	3
1¼	32	6	6	5½	3½	3
1½	40	6½	6	5½	3½	3½
2	50	7	6½	6	4	3½
2½	65	7½	7½	6½	4½	4
3	80	8	7½	7	4½	4
4	100	9	8½	7½	5	4½
6	150	10	9½	8½	6½	5½
8	200	11	10	9½	7½	6
10	250	12½	11	10½	8	7
12	300	13	12	10½	7½	6½

**NOTE :** The above information provides general guidelines. It should be used only as a reference and not as a guarantee of performance. Specific installation instructions and techniques may be required as a result of local plumbing and building codes, engineering specifications and instructions.



# EXPANSION AND CONTRACTION

uPVC pipes, like other piping materials, undergo length changes as a result of temperature variations above and below the installation temperature. They expand and contract 4.5 to 5 times more than steel or iron pipe. The extent of the expansion - contraction depends upon the coefficient of linear expansion of piping material. The length of pipe between directional changes, and the temperature differential.

The coefficient of thermal expansion (Y) for uPVC is  $3.1 \times 10^{-5}$  in./in./°F.

The amount of expansion or contraction can be calculated using the following formula :


$$\Delta L = Y(T_1 - T_2) \times L$$

$\Delta L$  = Dimensional change due to thermal expansion or contraction (in.)

Y = Expansion coefficient (in./in./°F)

(T<sup>1</sup>-T<sup>2</sup>) = Temperature differential between the installation temperature and the maximum or minimum system temperature, whichever provides the greatest differential (°F).

L = Length of pipe run between changes in direction (ft)



There are several ways to compensate for expansion and contraction. The most common methods are :

1. Expansion loops which consist of pipe and 90° elbows
2. Piston type expansion joints\*
3. Flexible bends\*
4. Bellows and rubber expansion joints\*

\*The manufacturers of these devices should be contacted to determine the suitability of their products for the specific application.

Expansion loops are a simple and convenient way to compensate for expansion and contraction when there is sufficient space for the loop in the piping system. A typical expansion loop design is shown below.

The length of leg "R" can be determined by using the following formula to ensure that it is long enough to absorb the expansion and contraction movement without damage. The length of leg "A" should be 1/2 the length of leg "R"

$$R = 1.44 D \Delta L$$

R = Expansion loop leg length (ft)


D = Nominal outside diameter of pipe (in).  
(See table below)

$\Delta L$  = Dimensional change due to thermal expansion or contraction (in).

When installing the expansion loop, no rigid or restraining support should be placed within the leg lengths of the loop. The loop should be installed as closely as possible to the mid-point between anchors. Piping support guides should restrict lateral movement and direct axial movement into the loop. Lastly, the pipe and fittings should be solvent cemented together, rather than using threaded connections.

Compensation for expansion and contraction in underground application is normally achieved by snaking the pipe in the trench. Proper trenching and burial procedures must be followed to protect the piping system.

The table below shows recommended offsets and loop lengths for piping up to 2½" nominal size.



Loop Length in Feet	MAX. TEMP. VARIATION °F, BETWEEN INSTALLATION									
	10°	20°	30°	40°	50°	60°	70°	80°	90°	100°
	LOOP OFFSET IN INCHES									
20	3.0	3.5	4.5	5.0	6.0	6.5	7.0	7.0	8.0	8.0
50	7.0	9.0	11.0	13.0	14.0	15.5	17.0	18.0	19.0	20.0
100	13.0	18.0	22.0	26.0	29.0	31.5	35.0	37.0	40.0	42.0

